

SAFETYZONE™ 

CLEAR SAFETY & SECURITY FILM



HanitaTek
Window Films

CLEAR
SAFETY & SECURITY FILM



SAFETYZONE™ CLEAR SAFETY & SECURITY WINDOW FILM

Hanita Coatings is recognized worldwide as a leading manufacturer of protective window films, designed to protect people and property from flying shards of glass.

SafetyZone's™ multilaminate safety and security films are renowned for their optical clarity and cleanliness—the result of top-grade polyester, our proprietary transparent adhesive, and tight adherence to demanding ISO 9001 quality-assurance standards. SafetyZone films are consistently distortion-free, and without the yellowish hue common to many other safety films on the market.

SafetyZone films are the professional installer's choice—for their performance, their installation flexibility, and their competitive prices.

Clear SafetyZone films are produced in 4, 7, 8 and 12 mil for resistance to impact, blast and natural disaster; with a special scratch-resistant coating for exterior applications. SafetyZone films are also available with the heat and glare protection of Silver, Matte and Cold Steel solar-control films.

SAFETYZONE: THE CLEAR SOLUTION FOR GLASS PROTECTION

- Holds broken glass together
- Durable scratch-resistant coating
- Totally transparent
- Aggressive PS adhesive
- Flexible multilayer construction

INTERNATIONAL GLASS SAFETY-STANDARDS ACCREDITATION:

- EN 12600
- CPSC 1201
- ANSI Z-97.1
- EN 356
- BS 6206
- DIN 52290
- GSA level C & D

S A F E T Y Z O N E

CLEAR SAFETY & SECURITY FILM



HanitaTek
Window Films

SAFETYZONE™

Optical & Solar Properties	4 Mil Clear	7 Mil Clear	8 Mil Clear	12 Mil Clear
Visible Light Transmitted	85%	85%	84%	83%
Visible Light Reflected	11%	11%	10%	10%
UV Radiation Rejected	90%	90%	93%	96%
Total Solar Energy Reflected	9%	10%	10%	11%
Total Solar Energy Transmitted	77%	76%	76%	74%
Total Solar Energy Absorbed	14%	14%	14%	15%
Shading Coefficient	0.93	0.91	0.92	0.9
Total Solar Energy Rejected	19%	20%	20%	22%

Optical & Solar Properties	4 Mil Anti-Graffiti	6 Mil Anti-Graffiti	4 Mil Clear Exterior SR
Visible Light Transmitted	85%	85%	86%
Visible Light Reflected	11%	11%	9%
UV Radiation Rejected	90%	93%	99%
Total Solar Energy Reflected	9%	10%	9%
Total Solar Energy Transmitted	77%	75%	78%
Total Solar Energy Absorbed	14%	15%	13%
Shading Coefficient	0.93	0.92	0.96
Total Solar Energy Rejected	19%	19%	19%

All solar performance data is based on film being applied to the inside of 1/4 inch clear monolithic annealed glass. All data reported has been measured, calculated and reported in accordance with ASTM, ASHRAE and AIMCAL standards. The data is subject to variations within accepted industry standards.

HANITATEK Tel: 800.660.5559 | www.hanitatek.com

